



## Hardwood Floor Timber Species Available

Commercial name	Botanical Name	Origin	Janka Hardness	Density (KD / 12%)
Chinese Acacia	Acacia confusa Merr.	Asia	2200psi	0.668g/cm <sup>3</sup>
Indonesia Acacia	Acacia leucophloea	Asia	1750psi	0.54g/cm <sup>3</sup>
American Walnut	Juglans nigra	America	1010psi	0.63g/cm <sup>3</sup>
Brazilian Teak	Dipteryx odorata	South America	3540psi	1.08g/cm <sup>3</sup>
Beli/Zebra	Microberlinia brazzavillensis	West Africa	1575psi	0.86g/cm <sup>3</sup>
Brazilian Walnut	Tabebuia	South America	3680psi	1.15g/cm <sup>3</sup>
North China Birch	Betula	Asia	1470psi	0.67g/cm <sup>3</sup>
Burma Walnut	Xylia spp.	Asia	2170psi	0.85g/cm <sup>3</sup>
Balau	Shorea laevis	Asia	1798psi	0.9g/cm <sup>3</sup>
Cumaru	Dipteryx odorata	South America	3540psi	1.08g/cm <sup>3</sup>
China Chestnut	Sweetia, panamensis	Asia	1450psi	0.75g/cm <sup>3</sup>
Ipe	Tabebuia	South America	3680psi	1.15g/cm <sup>3</sup>
Iroko	Chlorophora, excelsa	Africa	1260psi	0.68g/cm <sup>3</sup>
Kempas/Kambala	Koompassia, malaccensis	Asia	1710psi	0.75g/cm <sup>3</sup>
Merbau	Intsia	Asia	1712psi	0.85g/cm <sup>3</sup>
Black Locust	Robinia pseudoacacia	Asia	1700psi	0.77g/cm <sup>3</sup>
Oak	Quercus	Asia/Europe	1360psi	0.75g/cm <sup>3</sup>
Santos Mahogany	Myroxylon, balsamum	South America	2200psi	0.9g/cm <sup>3</sup>
Taun	Pometia	Asia	1900psi	0.68g/cm <sup>3</sup>
Teak	Tectona grandis	Asia	1155psi	0.68g/cm <sup>3</sup>

<http://hardwood-timberfloors.com>

<http://chinafloor.en.alibaba.com/>